
Evaporative Evolution of Brines from Synthetic Topopah Spring Tuff Pore Water, Yucca Mountain, NV

M. Alai, S. Carroll

This article was submitted to 2002 Fall Meeting of the Materials Research Society, Boston, MA, December 2-6, 2002

U.S. Department of Energy



November 26, 2002

Approved for public release; further dissemination unlimited

DISCLAIMER

This document was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor the University of California nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or the University of California, and shall not be used for advertising or product endorsement purposes.

This is a preprint of a paper intended for publication in a journal or proceedings. Since changes may be made before publication, this preprint is made available with the understanding that it will not be cited or reproduced without the permission of the author.

This work was performed under the auspices of the U.S. Department of Energy by the University of California, Lawrence Livermore National Laboratory under contract number W-7405-ENG-48.

This report has been reproduced directly from the best available copy.

Available electronically at http://www.doc.gov/bridge

Available for a processing fee to U.S. Department of Energy
And its contractors in paper from
U.S. Department of Energy
Office of Scientific and Technical Information
P.O. Box 62

Oak Ridge, TN 37831-0062 Telephone: (865) 576-8401 Facsimile: (865) 576-5728 E-mail: reports@adonis.osti.gov

Available for the sale to the public from U.S. Department of Commerce National Technical Information Service 5285 Port Royal Road Springfield, VA 22161 Telephone: (800) 553-6847

Facsimile: (703) 605-6900 E-mail: <u>orders@ntis.fedworld.gov</u>

Online ordering: http://www.ntis.gov/ordering.htm

OR

Lawrence Livermore National Laboratory Technical Information Department's Digital Library http://www.llnl.gov/tid/Library.html

Evaporative Evolution of Brines from Synthetic Topopah Spring Tuff Pore Water, Yucca Mountain, NV

Maureen Alai and Susan Carroll Lawrence Livermore National Laboratory, Livermore CA 94550

Abstract

We are investigating the evaporation of pore water representative of the designated high-level-nuclear-waste repository at Yucca Mountain, NV to predict the range of brine compositions that may contact waste containers. These brines could form potentially corrosive thin films on the containers and impact their long-term integrity. Here we report the geochemistry of a relatively complex synthetic Topopah Spring Tuff pore water that was progressively evaporated in a series of experiments. The experiments were conducted in a closed vessel, heated to 95°C, and purged with atmospheric CO₂. Aqueous samples of the evaporating solution were taken and analyzed to determine the evolving water chemistry, and the final solid precipitate was analyzed by X-ray diffraction.

The synthetic Topopah Spring Tuff water evolved towards a complex brine that contains about 3 mol% SO₄, and 2 mol% Ca, 3 mol% K, 5 mol% NO₃, 40 mol% Cl, and 47 mol% Na. Trends in the solution data and identification of CaSO₄ solids (anhydrite and bassanite) suggest that fluorite, carbonate, sulfate, and Mg-silicate precipitation minimize the corrosion potential of "sulfate type pore water" by removing F, Ca, and Mg during the early stages of evaporation

Introduction

Evaporative concentration experiments reported here investigate the evolution of the pore water found in rock formations within (Topopah Spring Tuff) and above (Paintbrush) the designated high-level-nuclear-waste repository at Yucca Mountain, NV. The primary goal of our experiments is to provide constraints on water chemistries and salt compositions that are likely to contact and react with the high-level waste canisters and any engineered canister shields. Once completed, our experimental work will also provide much needed data to test and validate the development of Pitzer data base and geochemical codes used by the Engineered Barrier System and the Unsaturated Zone to model the long-term performance of the repository.

The measured compositions of Yucca Mountain pore water vary, but can be generally placed into three types of waters that should evolve towards specific brine chemistry as the waters evaporate as the repository heats up (Figure 1):

1. Carbonate brine with alkaline pH Na-CO₃-Cl-SO₄

2. Sulfate brine with near neutral pH Na-Mg-Cl-SO₄

3. Ca-chloride brine with near neutral pH Na-Ca-Mg-Cl




Figure 1. Yucca Mountain pore waters as measured by Peterman and Yang (equivalent %).

Of concern to the Yucca Mountain Program, is that some of these pore waters could evolve to potentially corrosive CaCl₂, MgCl₂, and fluoride brines as well as the more benign carbonate and sulfate brines. The simple ratios of Ca, SO₄ and HCO₃ in Figure 1 illustrate the dominant carbonate and sulfate chemical divides that occur as waters evaporate (Eugster and Hardie, 1970; Eugster and Hardie, 1978, Li et al., 1997), but Figure 1 does not show important chemical divides for Mg, Si, or F. Nor does is show the relative magnitude of these salts to other major ions such as NO₃, which have shown to inhibit corrosion in mixed chloride-nitrate solutions (Brossia and Kelly, 1998). Temperature will also impact the evolution of the pore water. Recent modeling of Yucca Mountain pore water within the carbonate brine field at 25°C, evolved towards potentially corrosive Ca-chloride brines at 95°C, and not towards a more benign carbonate brine as predicted by Figure 1 (Bechtel SAIC Company, 2001).

Here we report our results for the evaporation of a synthetic Topopah Spring Tuff pore water at 95°C over a concentration range of 1x to ~400x.

Experimental Methods

Table 1 shows the chemical composition of the synthetic Topopah Spring Tuff pore water that was evaporated in three legs of this experiment. The chemical composition of the second leg was based on the brine composition towards the end of the first leg, and the composition of the third leg was based on the brine composition towards the end of the second leg. The solutions were prepared using analytical grade salts. Evaporation was conducted in a vented vessel heated to 95°C, and purged with atmospheric CO₂. The

extent of evaporation was monitored from the condensed water vapor vented from the reaction vessel. Periodic samples of the evaporating solution were filtered and analyzed **Table 1** Starting compositions for the evaporation of a synthetic Topopah Spring Tuff pore water.

	Leg 1 (Exp. FEC 9)	Leg 1 (Exp. FEC 9)	Leg 2 (Exp. FEC 12)	Leg 3 (Exp. FEC 13)
	molal 25°C	molal 95°C	molal 95°C	molal 95°C
F	5.95 x 10 ⁻⁵			
K ⁺	1.76 x 10 ⁻⁴	1.63 x 10 ⁻⁴	5.81 x 10 ⁻⁴	6.47×10^{-3}
NO_3	3.53 x 10 ⁻⁴	3.94 x 10 ⁻⁴	1.32×10^{-3}	1.17 x 10 ⁻²
Mg ⁺⁺	1.01×10^{-3}	6.48 x 10 ⁻⁴	6.04 x 10 ⁻⁴	1.05 x 10 ⁻³
SO ₄	1.23×10^{-3}	1.85×10^{-3}	4.64×10^{-3}	2.22 x 10 ⁻²
SiO ₂	1.39 x 10 ⁻³	9.21 x 10 ⁻⁴	1.98 x 10 ⁻³	2.22×10^{-3}
Ca ⁺⁺	1.57 x 10 ⁻³	1.25×10^{-3}	4.68×10^{-3}	2.15×10^{-2}
Na ⁺	2.84×10^{-3}	3.04×10^{-3}	1.10 x 10 ⁻²	1.10 x 10 ⁻¹
HCO_3	7.93 x 10 ⁻⁴	3.11 x 10 ⁻⁴	1.59 x 10 ⁻⁴	not analyzed
Cl ⁻	3.26×10^{-3}	3.31×10^{-3}	9.79 x 10 ⁻³	1.04 x 10 ⁻¹

to determine the evolving water chemistry. pH was measured at room temperature with a combination electrode, total dissolved carbon was measured with an infrared carbon analyzer, dissolved Ca, Mg, Si, and Na were measured with an inductively coupled plasma-atomic emission spectrometer, and dissolved K was measured using an atomic absorption spectrophotometer, and F, Cl, NO₃, and SO₄ anions were determined using ion chromatography. The solid precipitate was collected at the end of each leg of the experiment and analyzed by X-ray diffraction.

Results and Discussion

Our experimental results are summarized in Figures 2 and 3. The pore water composition appears to be controlled by the precipitation of a small amount of calcite removing all measurable dissolved CO₂ and the precipitation of anhydrite (CaSO₄) and/or bassanite (2CaSO₄•H₂O). These are the dominant chemical reactions predicted by chemical divide theory, which forms the basis for the Ca:HCO₃:SO₄ diagrams in Figures 1 and 2. Figure 2 shows the evolution of the water as it evaporated. The pore water evolved towards a SO₄ brine as predicted by chemical divide theory based on its initial Ca:SO₄:HCO₃ ratio. At the conclusion of the third leg (400x), the water composition had evolved to molar Ca: $SO_4 = 42:58$. It is important to note that sulfate concentrations will be minor compared to the concentration of Na, Cl, and NO, which have not be removed by mineral precipitation. At the conclusion of the third leg of this experiment, molar equivalents of Na and Cl were much greater than that of Ca and SO₄ (Na:K:Ca:Cl:SO₄:NO₃ = 47:3:2:40:3:5). Figure 2 also shows that a J-13 well water and a different Yucca Mountain unsaturated zone pore water (Rosenberg et al., 2001) evolve towards their respective Na-carbonate and Ca-chloride brines indicated by their initial Ca:SO_a:HCO₃ ratios. Although our results coupled with previous evaporation experiments (Rosenberg et al., 2001) suggest that Ca:SO₄:HCO₃ ternary diagrams can be used as a rough prediction of brines formed from dilute Yucca Mountain pore water, they do not capture

all of the important chemical divides that could affect the evolution of Yucca Mountain pore water such as fluorite and Mg-Silicate precipitation.




Figure 2. Evolution of a synthetic Topopah Spring Tuff pore water.

Figure 3 shows the evolution of the solution composition for all of the major elements comparing their relative concentrations to the concentration factor. The concentration factor is directly calculated from the amount of condensed water vapor during the evaporation experiment. Elements exhibit conservative concentration if they plot on the 1:1 correlation line and they exhibit removal by mineral precipitation if they plot below this line. The error bars in Figure 3 represent a 10% experimental uncertainty that reflects difficulties in synthesizing the "exact" solution composition from the end of one leg of the experiment to the beginning of the next leg. Figure 3 clearly shows the removal of Si, Ca, Mg, and SO₄. Amorphous silica precipitation and a Mg-silicate phase most likely controls the dissolved Si and Mg concentrations, which formed in the initial solution for leg 3. Dissolved SO₄ and Ca concentrations are controlled by sulfate precipitation as bassanite and/or anhydrite, which were identified in the X-ray diffraction patterns. In agreement with our results, Hardie and Eugster (1970) reported calcite, sepiolite (Mg₈H₆Si₁₂O₃₀(OH)₁₀•6H₂O), and gypsum(Ca₂SO₄•2H₂O) as early precipitates in saline lakes. The precipitation of both Mg and Ca as sulfate and/or silicates are important geochemical controls that will minimize the relative proportion of potentially corrosive Mg-chloride and Ca-chloride brines. The initial solution contained trace amounts of F which were rapidly removed from solution (data not shown) presumably as highly insoluble fluorite (CaF₂). This is an important geochemical control for F, a highly corrosive anion, and suggests that it will not threaten the integrity of the waste canisters or the drip shields in the repository. Figure 3b also suggests that there is some

precipitation of Cl and NO₃ above the predicted uncertainty. This mostly likely represents evaporation along the vessel walls as the water level drops, and the




Figure 3. Evolution of a synthetic Topopah Spring pore water plotted as measured sample:initial concentrations versus the concentration factor (see text for additional explanation).

experimental uncertainty reflecting the difficulty in synthesizing the exact solution from one leg to the other.

Conclusions

Our work shows that fluorite, carbonate, sulfate, and Mg-silicate precipitation minimize the corrosion potential of "sulfate type pore water" by removing F, Ca, and Mg during the early stages of evaporation, yielding a Na-K-Cl-SO₄-NO₃ brine. Future work includes continued evaporation of this water and other sulfate, calcium chloride, and carbonate waters indicated in Figure 1 from 1 X to 10,000 X to determine Yucca Mountain pore water evolution during evaporation and to test the Pitzer data base and geochemical models.

References

Bechtel SAIC Company (2001) FY01 Supplemental Science and Performance Analysis, V. 1 Scientific Basis and Analyses, Report #TDR-MGR-MD-000007 REV 0, p. 6-56 to 6-59.

Brossia, C. S. and Kelly, R. G. (1998) Influence of alloy sulfur content and bulk electrolyte composition on crevice corrosion initiation of austenitic stainless steel. *Corrosion*, 54, 145-154.

Eugster, H.P., Hardie, L.A., 1978. Saline lakes. In: Lerman, A. (Ed.), Lakes: Chemistry, Geology, Physics, Springer-Verlag, New York.

Hardie, L.A., Eugster, H. P., 1970. The evolution of closed-basin brines. *Mineral Society Amer. Spec. Pap.* 3, 273-290.

Li, J., Lowenstein, T. K., and Blackburn, I. R. (1997) Responses of evaporite mineralogy to inflow water sources and climate during the past 100 k.y. in Death Valley, California. *GSA Bulletin*, **109**, 1361-1371.

- Rosenberg, N.D., Gdowski, G. E.., 2000. Evaportive chemical evolution of natural waters at Yucca Mountain, Nevada. *Applied Geochemistry*, 16, 1231-1240.
- Yang, I. C., Rattray, G. W., and Yu, P. (1996) Interpretation of Chemical and Isotopic Data From Boreholes in the Unsaturated Zone at Yucca Mountain, Nevada. USGS, Water-Resources Investigations Report 96-4058 (Tables 2 and 3).